



US008691889B2

(12) **United States Patent**
Gozum et al.

(10) **Patent No.:** **US 8,691,889 B2**
(45) **Date of Patent:** ***Apr. 8, 2014**

(54) **LIGHTWEIGHT WALL REPAIR
COMPOUNDS**

(71) Applicant: **3M Innovative Properties Company**,
St. Paul, MN (US)

(72) Inventors: **John E. Gozum**, Stillwater, MN (US);
Richard A. Mallo, Woodbury, MN (US)

(73) Assignee: **3M Innovative Properties Company**,
St. Paul, MN (US)

(*) Notice: Subject to any disclaimer, the term of this
patent is extended or adjusted under 35
U.S.C. 154(b) by 0 days.

This patent is subject to a terminal dis-
claimer.

(21) Appl. No.: **13/938,770**

(22) Filed: **Jul. 10, 2013**

(65) **Prior Publication Data**

US 2013/0296462 A1 Nov. 7, 2013

Related U.S. Application Data

(62) Division of application No. 12/997,212, filed as
application No. PCT/US2009/045778 on Jun. 1, 2009,
now Pat. No. 8,507,587.

(60) Provisional application No. 61/061,274, filed on Jun.
13, 2008.

(51) **Int. Cl.**
C08J 9/32 (2006.01)

(52) **U.S. Cl.**
USPC **523/218**; 523/219; 523/220

(58) **Field of Classification Search**
USPC 523/218, 219, 220
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

3,386,223 A 6/1968 Wegwerth
3,907,725 A 9/1975 Forte et al.

4,283,320 A	8/1981	Carroll et al.
4,391,647 A	7/1983	Deer et al.
4,629,751 A	12/1986	Montgomery
4,824,879 A	4/1989	Montgomery et al.
4,904,709 A	2/1990	Hermele
5,112,400 A	5/1992	Nae et al.
5,336,318 A	8/1994	Attard et al.
5,863,975 A	1/1999	Whitton et al.
6,358,309 B1	3/2002	Langford
7,037,865 B1	5/2006	Kimberly
8,507,587 B2 *	8/2013	Gozum et al. 523/218
2006/0096074 A1	5/2006	Foster et al.
2006/0142456 A1	6/2006	Langford

FOREIGN PATENT DOCUMENTS

JP	H06-287544	10/1994
JP	H07-278463	11/1994
JP	2002-531369	9/2002
WO	WO 00/34200	6/2000

OTHER PUBLICATIONS

3M Material Safety Data Sheet: 3M Brand Spakfast Wall Repair
Compound.

3M Material Safety Data Sheet: 3M Wall Repair Compound.
Gozum, John E., U.S. Appl. No. 13/938,801, filed Jul. 10, 2013.
International Search Report, PCT/US2009/045778, mailed Jan. 12,
2010, 3 pages.

* cited by examiner

Primary Examiner — Edward Cain

(74) *Attorney, Agent, or Firm* — Kenneth B. Wood

(57) **ABSTRACT**

Herein are disclosed wall repair compounds comprising at least one or more polymeric binder latex emulsions, one or more inorganic fillers, and comprising an amount of organic polymeric thickener that is less than about 0.1 percent by weight based on the total weight of the wall repair compound. In certain embodiments, the wall repair compound comprises an inorganic filler system selected such that such that synthetic inorganic fillers comprise essentially 100 percent of the inorganic filler used. In certain embodiments, the wall repair compound comprises one or more glycol ether smoothing agents.

19 Claims, No Drawings